



TECHNICAL DATA SHEET

Safoam® RAZ-110P

Chemical Blowing Agent

DESCRIPTION

Exothermic chemical blowing agent powder used to create cellular structure in thermoplastics. Especially suited for crosslink applications.

Minimum Processing Temperature:	190°C (375°F)
Gas Yield:	125 ml/g
Appearance:	Free Flowing Light Orange Powder
Odor:	Faint odor

Data is provided for reference only. Consult your Reedy Chemical Foam Technical Sales Representative for dosing instructions specific to your product and process.

This information has been compiled with the utmost care and is intended to provide general information on our products and their uses. It should not therefore be construed as guaranteeing specific properties of the products described. Customers must make their own determination that their use of our product(s) is safe, lawful, and technically suitable for their intended application(s). The right to adapt the information at any time to new developments is reserved. Intellectual property rights must be observed.

All information and including technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed by you that you hold us harmless from all liability in connection with the use of our products, technical assistance, and information. In no event shall Reedy Chemical Foam be liable for any incidental, consequential or special damages, or loss of profit.